

## DIN20022 2SN



<b>Inner Tube</b>	<b>Reinforcement</b>	<b>Cover</b>	
Smooth synthetic rubber resistant to oils and water	2 high tensile steel braids	Synthetic rubber resistant to oils and weather agents	
<b>Specifications</b>	<b>Approvals</b>	<b>Applications</b>	<b>Temperature</b>
EN 853 2SN	GL, LR, LOBA (a richiesta - upon request)	Medium/high pressure lines	from -40°C (-40°F) to 100°C (212°F) Max 125°C (257°F)
<b>Recommended Fluids</b>		<b>Tolerances</b>	<b>Lengths</b>
Mineral oils, vegetable and colza oils, glycol and polyglycol based oils, synthetic ester based oils, oils in water emulsion, water, mineral lubricants, diesel fuels (up to 93°C).		According to the Norms	Manufacturing coils
<b>Branding</b>		<b>Performances</b>	
<b>white / ink:</b> RAPISARDA DINAMIC 2SN EN 853 - 2SN xx xxxx BAR WP <b>ITALY Reverse:</b> Q/Y - Production lot no.		Resistance to burst over the norms. Sizes 2.3/8" 2.1/2" and 3" available upon request.	

I.D.				O.D.			Working Pressure	Burst Pressure		Actual Burst Pressure		Bending Radius		Weight	
Dn	dash	mm	inch	mm	inch	bar	psi	bar	psi	bar	psi	mm	inch	g/mt	lb/ft
5	-3	4,8	3/16	13,4	0,527	415	6020	1650	23930	1750	25360	90	3,5	289	0,194
6	-4	6,4	1/4	15	0,590	400	5800	1600	23200	1840	26660	100	4	376	0,252
8	-5	8	5/16	16,6	0,635	350	5075	1400	20300	1460	21160	115	4,5	412	0,277
10	-6	9,5	3/8	19	0,748	330	4785	1320	19140	1440	20870	130	5	519	0,346
12	-8	12,7	1/2	22,2	0,874	275	3990	1100	15960	1220	17680	180	7	630	0,423
16	-10	16	5/8	25,4	1,000	250	3625	1000	14500	1150	16665	200	8	780	0,523
20	-12	19	3/4	29,3	1,153	215	3120	850	12480	1010	14640	240	9,50	959	0,643
25	-16	25,4	1	38,1	1,512	165	2395	650	9570	720	10430	300	12	1409	0,945
32	-20	31,8	1 1/4	48,3	1,901	125	1810	500	7240	560	8115	420	16,5	2059	1,381
40	-24	38,1	1 1/2	54,6	2,150	90	1305	360	5220	450	6520	500	20	2385	1,6
50	-32	50,8	2	67,3	2,650	80	1160	320	4640	330	4780	630	25	3050	2,046